

Metal Impex – 309LMo TIG / MIG / SAW Welding Filler Wires

Classifications:

EN ISO 14343-A: W 23 12 2 L
AWS A5.9: ~ ER 309LMo

EN ISO 14343-B: SS 309LMo

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Mo	Si
<0.03	21.00 – 25.00	12.00 - 14.00	1.00 – 2.50	2.00 – 3.50	0.30 - 0.65

Description:

- For dissimilar welding of austenitic stainless steels and mild or low-alloy steels and welding difficult to weld hardenable or heat treatable steels.

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 350	min. 550	min. 25

Packaging:

MIG/MAG Wire (Ø in mm): 0.80 / 1.00 / 1.20 MM in 12.50 Kg Spools / 125 Kg Drums
TIG Wire (Ø in mm): 0.80 / 1.00 / 1.20 / 1.60 / 2.00 / 2.40 / 3.20 / 4.00 MM
SAW Wire (Ø in mm): 1.60 / 2.00 / 2.40 / 3.20 / 4.00 / 5.00 MM

Metal Impex

- 📍 Shop No. 1 Ground Flr. 23, 3rd Khetwadi Lane, Kotwala Bldg. MUMBAI - 400 004.
☎ 02267494777, 02266363150
📞 +91 9967568729
✉ metalexim@hotmail.com, narendra@metalimpex.co.in