

Metal Impex – ER 309LSi TIG / MIG / SAW Welding Filler Wires

Classifications:

EN ISO 14343-B: SS 309L
AWS A5.9: ER309L

KS D 7026: Y309L
JIS Z 3321: Y309L

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si
<0.03	23.00 – 25.00	12.00 - 14.00	1.00 - 2.50	0.65 – 1.00

Description:

- For Welding of 22%Cr-12%Ni STS and dissimilar steels such as 304L to mild steels or low alloy steels.

Typical Mechanical Properties:

Yield Strength (Mpa) min. 350	Tensile Strength (Mpa) min. 550	Elongation (%) min. 35
-------------------------------------	---------------------------------------	------------------------------

Packaging:

MIG/MAG Wire (Ø in mm): 0.80 / 1.00 / 1.20 MM in 12.50 Kg Spools / 125 Kg Drums
TIG Wire (Ø in mm): 0.80 / 1.00 / 1.20 / 1.60 / 2.00 / 2.40 / 3.20 / 4.00 MM
SAW Wire (Ø in mm): 1.60 / 2.00 / 2.40 / 3.20 / 4.00 / 5.00 MM

Metal Impex

📍 Shop No. 1 Ground Flr. 23, 3rd Khetwadi Lane, Kotwala Bldg. MUMBAI - 400 004.

☎ 02267494777, 02266363150

📞 +91 9967568729

✉ metalexim@hotmail.com, narendra@metalimpex.co.in