

Metal Impex – ER 317L

Classifications:

EN ISO 14343-B: 2007: SS 317L
AWS A5.9-07: ER317L

KS D 7026: 2005: Y317L
JIS Z 3321: 2008: Y317L

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si	Mo
<0.03	18.50 – 20.50	13.00 – 15.00	1.00 - 2.50	0.30 – 0.65	3.00 – 4.00

Description:

- TIG welding of 20%Cr-14%Ni-3.5Mo austenite stainless steels (AISI STS 316, 316L, 317)

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 300	min. 520	min. 30

Metal Impex

📍 Shop No. 1 Ground Flr. 23, 3rd Khetwadi Lane, Kotwala Bldg. MUMBAI - 400 004.

☎ 02267494777, 02266363150

📞 +91 9967568729

✉ metalexim@hotmail.com, narendra@metalimpex.co.in