

Metal Impex – ER 347Si

Classifications:

EN ISO 14343-B: 2007: SS 347Si
AWS A5.9-07: ER347Si

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si
<0.08	19.00 – 21.50	9.00 – 11.00	1.00 – 2.50	0.65 – 1.00

Description:

- TIG welding of 20%Cr-10%Ni-Nb austenite stainless steels (AISI STS 347, 321)

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 350	min. 550	min. 35

Metal Impex

📍 Shop No. 1 Ground Flr. 23, 3rd Khetwadi Lane, Kotwala Bldg. MUMBAI - 400 004.

☎ 02267494777, 02266363150

📞 +91 9967568729

✉ metalexim@hotmail.com, narendra@metalimpex.co.in