

Metal Impex – ER 410

Classifications:

EN ISO 14343-B: 2007: SS 410
AWS A5.9-07: ER410

KS D 7026: 2005: Y410
JIS Z 3321: 2008: Y410

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si
<0.12	11.50 – 13.50	<0.60	<0.60	<0.50

Description:

- MIG / TIG welding of 12%Cr martensite stainless steels. (AISI STS 403, 410)

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 250	min. 520	min. 20

Metal Impex

📍 Shop No. 1 Ground Flr. 23, 3rd Khetwadi Lane, Kotwala Bldg. MUMBAI - 400 004.

☎ 02267494777, 02266363150

📞 +91 9967568729

✉ metalexim@hotmail.com, narendra@metalimpex.co.in