

Metal Impex – ER 430L

Classifications:

EN ISO 14343-B: 2007: SS 430L
AWS A5.9-07: ER430L

Typical Chemistry Composition of Weld Deposit:

C	Cr	Ni	Mn	Si
<0.10	15.50 – 17.00	<0.60	<0.60	<0.50

Description:

- MIG / TIG welding of 16%Cr-Nb ferrite stainless steels. (AISI 405, 410L, 429, 430, 444)

Typical Mechanical Properties:

Yield Strength (Mpa)	Tensile Strength (Mpa)	Elongation (%)
min. 220	min. 410	min. 15

Metal Impex

📍 Shop No. 1 Ground Flr. 23, 3rd Khetwadi Lane, Kotwala Bldg. MUMBAI - 400 004.

☎ 02267494777, 02266363150

📞 +91 9967568729

✉ metalexim@hotmail.com, narendra@metalimpex.co.in