

Metal Impex NiCrMo-13 MIG / TIG Welding Wires

Classifications:

ISO 18274: NiCr23Mo16/Ni 6059
W.Nr.: 2.4605

AWS A5.14/ASME SFA-5.14: ERNiCrMo-13

Typical Chemistry Composition of Weld Deposit:

C	Si	Mn	Cr	Ni	Mo	Al	Fe
<0.01	<0.05	<0.10	25.00	Remainder	15.00	<0.30	<0.20

Description:

- EWB® 59 is a nickel-chrome-molybdenum alloy with excellent wet corrosion resistance for the most demanding applications.
- It combines excellent corrosion resistance in oxidizing and reducing media, has excellent resistance in chloride containing media and to localized corrosion environments.
- EWB® 59 has excellent thermal stability compared to other common nickel alloys and has therefore outstanding resistance to inter metallic precipitation during welding.

Typical Mechanical Properties:

Yield Strength	Tensile Strength	Elongation
(Mpa)	(Mpa)	(%)
470	750	40

Packing Available:

TIG Wire (Ø in mm): 1.60 / 2.40 / 3.20 / 4.00

Metal Impex

📍 Shop No. 1 Ground Flr. 23, 3rd Khetwadi Lane, Kotwala Bldg. MUMBAI - 400 004.

☎ 02267494777, 02266363150

📞 +91 9967568729

✉ metalexim@hotmail.com, narendra@metalimpex.co.in